

PUre Cooling 36

- **polyurethane heat-conducting paste**
 - **high-performance and electrically insulating**
 - **silicon-free and solvent-free**
 - **excellent thermal conductivity**
 - **no metallic fillers**
 - **high-long-term stability**
 - **good creeping properties**
 - **ideal for different cooling applications, improves the heat-transfer**
-

Product specification:

Operating temperature:	-60°C up to +200°C	
Type:	non-curing and non-drying paste	
Viscosity (23°C):	paste: PUre Cooling 36	200.000 - 250.000 mPa*s
Density (22°C):	paste: PUre Cooling 36	2,10 - 2,30 g/cm ³
Colour:	nature or as required	

Physical properties:

Thermal conductivity:	3,6 W/m*K	DIN EN ISO 22007
Thermal resistance:	no blooming after 4h at 200°C	

Electrical properties:

Dielectrical strength:	30 kV/mm	IEC 60243-1, VDE 0303, TI.2
Volume resistance:	10 ¹⁶ Ω*cm (23°C/ 50% r.F.)	IEC 60243-1, VDE0303, TI.30

- Shelf life: 6 months in sealed original containers when stored in dry conditions (15°C to 25°C).
- Packaging: Resin and hardener are offered in separate packaging units.
- RoHS: We hereby certify that all our products are unexceptional RoHS conform, according to the EU directive 2011/65/EG (RoHS2).