

PUre Transparency ST 43/30

- 2-components polyurethane casting resin
- solvent-free system
- crystal clear and UV-resistant
- transmission values over 90 %
- soft curing degree
- excellent adhesive properties
- ideal for LED applications
- **TIP: good combination possibilities with kisling's opaque and thermal conductive casting resins**

✓ The casting resin is used with **PUre Hardener 3000**

✓ Product name explanations:

PUre Transparency = product line
ST 43 = product name
/30 = potlife configuration in min


Product specification:

Operating temperature:	-40°C up to +130°C	no affect of the physical properties
	-40°C up to + 90°C	no affect of the optical properties
Flammability classification:		
Mixing ratio:	100 parts PUre Transparency ST 43/30 60 parts PUre Hardener 3000	
Viscosity (22°C):	resin: PUre Transparency ST 43/30	750 - 950 mPa*s
	hardener: PUre Hardener 3000	450 - 750 mPa*s
	mixing viscosity	700 - 900 mPa*s
Density (22°C):	resin: PUre Transparency ST 43/30	1,05 - 1,10 g/cm ³
	hardener: PUre Hardener 3000	1,10 - 1,15 g/cm ³
Colour:	Crystal clear	
Potlife:	30 - 45 minutes The curing time depends on the thickness of the layer, the casting volume and the temperature.	
Curing time (22°C):	16 - 30 hours	
Final hardness	10 - 14 days	

Physical properties:

Shore-Hardness:	A 25 - 40	ISO 868, DIN 53505
Thermal conductivity:	0,2 W/m*K	DIN EN ISO 22007
Glass transition temperature:	-30,2°C	TMA
Coefficient of expansion:	101,1 ppm/K 199,8 ppm/K	< Tg, TMA > Tg, TMA
Shrinkage after curing:	<1 %	
Water absorption:	0,2 % (30 days at 23°C)	
Insulation class:	B	IEC 60085

Transmission values:



- Shelf life: 6 months in sealed original containers when stored in dry conditions (15°C to 25°C).
- Packaging: Resin and hardener are offered in separate packaging units.
- RoHS: We hereby certify that all products are unexceptional RoHS conform according to the EU-directive 2011/65/EG (RoHS2) and the amendment of Directive 2015/863.

Our technical advice, whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and therefore, entirely your own responsibility. Should in spite of this, liability be established by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.