

## GapFiller

### Resin 8792 (ex GF92) + Hardener 8992 (ex G4092)

- **2-components polyurethane GapFiller**
- **solvent-free system**
- **high thermal conductivity and electrically insulating**
- **no metallic fillers**
- **no halogenated flame-retardants**
- **ideal for heat-reduction of battery systems, power electronics and high performance components**

#### Product specification:

Mixing ratio:	Resin 8792	100 volume parts
	Hardener 8992	100 volume parts
Viscosity (22°C):	Resin 8792	70'000 – 90'000 mPa·s
	Hardener 8992	80'000 – 100'000 mPa·s
	Mixing viscosity	75'000 – 95'000 mPa·s
Density (22°C):	Resin 8792	2.40 – 2.50 g/cm <sup>3</sup>
	Hardener 8992	2.40 – 2.50 g/cm <sup>3</sup>
Colour:	Nature (beige)	
Pot life:	20 – 30 minutes	
Curing time (22°C):	24 – 48 hours	
Final hardness	10 – 14 days	

**Physical properties:**

Shore-Hardness:	A 40 – 50	ISO 868, DIN 53505
Thermal conductivity:	2.0 W/(m·K)	DIN EN ISO 22007
Glass transition temperature:	-62.3°C	TMA
Coefficient of expansion:	29.6 ppm/K	< T <sub>g</sub> , TMA
	183.4 ppm/K	> T <sub>g</sub> , TMA
Shrinkage after curing:	<1 %	
Water absorption:	0.4 % (30 days at 23°C)	
Operating temperature:	-55°C up to +130°C	
Flammability classification:	V-0 in 4.0 mm	

Shelf life:	6 months in sealed original containers when stored in dry conditions (15°C to 25°C).
Packaging:	Resin and hardener are offered in cartridges or separate packaging units on request.

Our technical advice, whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and therefore, entirely your own responsibility. Should in spite of this, liability be established by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.

TDS\_8792+8992\_e/PC/27.02.2023