

GapFiller

Resin 8793 (ex GF93) + Hardener 8993 (ex G4093)

- 2-components polyurethane GapFiller
- solvent-free system and electrically insulating
- excellent thermal conductivity
- no metallic fillers
- no halogenated flame-retardants
- excellent adhesive properties
- ideal for heat-reduction of battery systems, power electronics and high performance components

Product specification:

Mixing ratio (volume):	Resin 8793	100 parts
	Hardener 8993	100 parts
Viscosity (22°C): (At 10 rpm)	Resin 8793	70'000 – 90'000 mPa·s
	Hardener 8993	80'000 – 100'000 mPa·s
	Mixing viscosity	70'000 – 100'000 mPa·s
Density (22°C):	Resin 8793	2.20 – 2.30 g/cm ³
	Hardener 8993	2.20 – 2.30 g/cm ³
Colour:	Nature (beige)	
Pot life:	20 – 30 minutes	
Curing time (22°C):	24 – 48 hours	
Final hardness	10 – 14 days	

Physical properties:

Shore-Hardness:	A 60 – 70	ISO 868, DIN 53505
Thermal conductivity:	3.0 W/(m·K)	DIN EN ISO 22007
Glass transition temperature:	-65.7 °C	TMA
Coefficient of expansion:	47.2 ppm/K 158.3 ppm/K	< Tg, TMA > Tg, TMA
Shrinkage after curing:	<1 %	
Water absorption:	0.4 % (30 days at 23°C)	
Insulation class:	B	IEC 60085
Operating temperature:	-40°C up to +130°C	
Flammability classification:	V-0 in 4.0mm	

Shelf life:	6 months in sealed original containers when stored in dry conditions (15°C to 25°C).
Packaging:	Resin and hardener are offered in separate packaging units.
RoHS:	We hereby certify that all our products are unexceptional RoHS conform, according to the EU directive 2011/65/EG (RoHS2) and the amendment of Directive 2015/863.

TDS_8793+8993/PC/07.09.2022