

### **Transparency**

## Resin 8812/30T (ex ST 45) + 8930 (ex 3000)

- 2-components polyurethane casting resin
- Solvent-free system
- Crystal clear and UV-resistant
- Transmission values over 90 %
- Hard curing degree
- · Excellent adhesive properties
- Ideal for LED applications
- TIP: good combination possibilities with Kisling's opaque and thermal conductive casting resins

#### **Product specification:**

Mixing ratio (weight):	Resin 8812/30T	100 parts	
	Hardener 8930	166 parts	
Viscosity (22°C):	Resin 8812/30T	1'600 – 2'000 mPa·s	
	Hardener 8930	450 - 750 mPa·s	
	Mixing viscosity	850 - 1'250 mPa·s	
Density (22°C):	Resin 8812/30T	1.03 - 1.08 g/cm³	
	Hardener 8930	1.10 - 1.15 g/cm³	
Colour:	Crystal clear		
Pot life:	30 – 45 minutes		
	The curing time depends on the thickness of the layer, the		
	casting volume and the temperature.		
Curing time (22°C):	16 - 30 hours		
Final hardness	10 - 14 days		




### **Physical properties:**

Shore-Hardness:	D 68 - 72	ISO 868, DIN 53505
Thermal conductivity:	0.2 W/(m·K)	DIN EN ISO 22007
Glass transition temperature:	32.2 °C	TMA
Coefficient of expansion:	95.1 ppm/K 188.8 ppm/K	< Tg, TMA > Tg, TMA
Shrinkage after curing:	<1 %	
Water absorption:	0.2 % (30 days at 23°C)	
Operating temperature:	-40°C up to +130°C (no effect on the physical properties) -40°C up to + 90°C (no effect on the optical properties)	

#### **Transmission values:**

Transmission measured against air, layer thickness approx. 8 mm, Analytik Jena Specord S 100



Kisling (Deutschland) GmbH | Salzstraße 15 | 74676 Niedernhall | Germany
Mail address: Waldstraße 15 | 71139 Ehningen | Germany
P +49 7940 50961 61 | info@kisling.com | www.kisling.com
Registered office in Künzelsau, Registration court Stuttgart HRB 571451 | VAT: DE 213 424 398
CEO: Dr. Dirk Clemens | Thomas Isleib
Deutsche Bank AG, Heilbronn | IBAN: DE89 6207 0081 0015 4385 00 | BIC: DEUTDESS620



# BONDING + SEALING + ENCAPSULATION



Shelf life:

6 months in sealed original containers when stored in dry conditions (15°C to 25°C).

Packaging:

Resin and hardener are offered in separate packaging units.

Our technical advice, whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and therefore, entirely your own responsibility. Should in spite of this, liability be established by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.

TDS\_8812\_30T+8930\_e/PC/09.05.2023