



Kisling AG

**Motorenstrasse 102
CH-8620 Wetzikon**

Telefon +41 (0)58 272 01 01
Telefax +41 (0)58 272 01 03

info@kisling.com
www.kisling.com

TECHNICAL DATA SHEET

ergo® 1810 (ergo® 1811 resin + ergo® 1812 activator)

Product - Description

The product is suitable to bond metals like aluminum, steel, brass and its alloys as well as ferrite and combinations.

It is a two-component system and cures after mixing into a tack-free, high-strength and impact resisting polymer film. The best mixture-ratio is 1:1 (volume) and is obtainable without problems by using the common double-cartridges.

Advantages

- Fast curing system
- High tensile shear strength
- Creates a dry and tack-free film, even outside the bonding area
- Resists against impacts as well as again peeling
- Good gap-filling behavior up to 0,50mm
- Free of solvents
- Short fixture time and reliable curing

Physical Properties (liquid product)

Chemical base : modified urethane-methacrylate

Viskosity : thixotropic

Brookfield RVT, Sp.6, 25°C, 1rpm : approx. 150.0 00 mPas

100rpm : approx. 5.000 mPas

Density : 1,1 g/cm³

color adhesive (ergo® 1811) : red

activator (ergo® 1812) : green

Shelf life : 12 month at room temperature



Kisling AG

**Motorenstrasse 102
CH-8620 Wetzikon**

Telefon +41 (0)58 272 01 01
Telefax +41 (0)58 272 01 03

info@kisling.com
www.kisling.com

- 2 -

cured product:

tensile shear strength acc. to DIN EN 1465, parts only degreased

aluminum/ aluminum

after 24 h at 23°C : > 25 N/mm²

steel/ steel

after 24 h at 23°C : > 25 N/mm²

Impact resistance : good
Resistance against bending : very good
Elongation at break : ~ 50 %
Peeling (T-peel on aluminium) : ~ 6 N/mm
Thermal range : - 40°C up to + 150°C

Curing

Curing system : 2-component-system
ratio 1:1 (volume)
Potlife : 2 - 5 minutes (2g-mixture)
Initial strength : ~ 10 minutes at 23°C
75% of final strength : ~ 2 hours at 23°C
Final strength : ~ 12 hours at 23°C
Dry, tack-free surface : ~ 12 hours at 23°C

How to use the product

Resin ergo® 1811 und activator ergo® 1812 is normally applied by using the double-cartridge with static mixture tube. ATTENTION: Potlife in the tube will be, depending on room-temperature, between 2 - 5 minutes. Apply the mixed glue on one part and spread it carefully over the whole bonding area. Fit the parts together and fix them at least as long as the potlife time, better 10 minutes.

WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KISLING products are safe, effective, and fully satisfactory for the intended end use. KISLING sole warranty is that the product will meet the KISLING sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. KISLING specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KISLING provides you with a specific, duly signed endorsement of fitness for use, KISLING disclaims liability for any incidental or consequential damages. Suggestions of uses should not be taken as inducements to infringe any particular patent.