



Telefon +41 (0)58 272 01 01 Telefax +41 (0)58 272 01 03 info@kisling.com www.kisling.com

TECHNICAL DATA SHEET ergo 4102

Thread Locker, high strength

Description

Fastener for stud bolts, ball and roller bearings which shall not be disassembled later on.

Physical Properties (liquid product) Chemical Base: Diester of Methacrylic Acid Colour: red Viscosity: 25°C Brookfield RVT 500 – 900 mPas spindle/ rpm 2/201.11 g/cm³ 25°C Density: Max. thread diameter: M 25 Max. gap filling: 0.15 mm Flash point: > 100°C Shelf life: 1 year at room temperature

Physical Properties (cured product)

Measured on M10 x 20 bolt - grade 8.8 zinc galvanised - nut 0.8d (no on-torque)

| Initial strength after: Functional strength after: Final strength after: | 5 - 15 minutes 1 - 3 hours 5 - 10 hours | |
|--|---|-----------|
| Loose-break torque: Prevailing torque: | > 30 Nm (M10) > 40 Nm (M10) | DIN 54454 |
| Shear strength: | > 20 N/mm² | DIN 54452 |
| Thermal range: | - 55°C up to +150°C | |

WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KISLING products are safe, effective, and fully satisfactory for the intended end use. KISLING sole warranty is that the product will meet the KISLING sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. KISLING specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KISLING provides you with a specific, duly signed endorsement of fitness for use, KISLING adapted and as the taken as inducements to infringe any particular patent.