



TECHNICAL DATA SHEET

ergo.[®] 6205 Hybrid-Polymer

Fast curing, elastic single-component sealant and adhesive for bonding as well as sealing of seams and joints in carbody-, waggon-, container and boatbuilding. Also suitable for mechanical engineering and applications in air-conditioners and ventilation technologies.

Advantages

- good adhesion to glass, a wide range of metal (zinc, aluminium, steel), varnished and primed surfaces
- good adhesion to wooden as well as to mineral substrates and to thermoplastics (except PE, PP, PTFE)
- resistant against humidity, weathering and temperatures from -40°C up to +90°C (up to +120°C for short intervals)

Properties of liquid product

Chemical Base	Hybrid-Polymer
Appearance blade, stable	pasty, spreadable with a
Colour ergo. [®] 6205	black
Density at 23°C	~ 1,44 g/cm ³
Viscosity @ 25°C (EN 12092, Cone-plate-system, MK25) shear rate 10 s ⁻¹ 100 s ⁻¹	110.000 – 130.000 mPa•s 40.000 – 50.000 mPa•s
Skinning time at 23°C/50%rh (pre-tests under real ambient conditions are recommended)	~ 10 minutes
Curing progress at 23°C/50%rh	after 24 h : ~ 3 mm
Change of weight (after 14 days)	~ 1 %

Typical properties of cured product

Tensile strength (DIN 53504) storage 7 days at 23°C/50%rh	~ 3,0 N/mm ²
Elongation at break (DIN 53504) storage 7 days at 23°C/50%rh	~ 500 %



Kisling AG

**Motorenstrasse 102
CH-8620 Wetzikon**

Telefon +41 (0)58 272 01 01
Telefax +41 (0)58 272 01 03

info@kisling.com
www.kisling.com

- 2 -

Modulus at 100% elongation and 23°C (DIN 53504 S2) ~ 1,0 N/mm²
storage 7 days at 23°C/50%rh

Tear resistance (ASTM D 624, Form B) ~ 20 N/mm
storage 7 days at 23°C/50%rh

Shore-A-hardness (DIN 53505) ~ 42
storage 28 days at 23°C/50%rh

Thermal range -40°C up to +90° C
(short intervals up to +120°C)

Working temperature +5°C up to +30°C

Packaging cartridges à 310 ml

Storage conditions cool and dry
(no longer periods > +25°C)

Storage stability 15 month in original box

Usage

Good adhesion to clean, dry and grease-free surfaces (cleaned either with **ergo.® 9190** or **ergo.® 9195**), even without Primer. For best results we recommend the use of Primer **ergo.® 6950** (non absorbing surfaces) or of Primer **ergo.® 6960** (absorbing surfaces) Please check the compatibility with varnish and plastic in advance

Apply **ergo.® 6205** with a common putty gun. The thickness of the needed layer depends on expected forces and relative movements. The curing process is influenced by layer thickness, temperature and humidity

Safety

Please read our MSDS and the labels carefully before use

WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KISLING products are safe, effective, and fully satisfactory for the intended end use. KISLING sole warranty is that the product will meet the KISLING sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. KISLING specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KISLING provides you with a specific, duly signed endorsement of fitness for use, KISLING disclaims liability for any incidental or consequential damages. Suggestions of uses should not be taken as inducements to infringe any particular patent.