

Page 1/8

Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 10.04.2023 Version number 3 (replaces version 2) Revision: 10.04.2023 SECTION 1: Identification of the substance/mixture and of the company/undertaking - 1.1 Product identifier - Trade name: 1090 - 1.2 Relevant identified uses of the substance or mixture and uses advised against No further relevant information available. - Application of the substance / the mixture Adhesives - 1.3 Details of the supplier of the safety data sheet - Manufacturer/Supplier: Kisling AG Motorenstrasse 102 CH-8620 Wetzikon Tel: +41- 58-272 0 272 - Further information obtainable from: Product safety department - Department issuing MSDS: info@kisling.com - 1.4 Emergency telephone number: Tox Info Suisse: 145 / +41-44-2 51 51 51 +49-700-24 112 112 (KAR) +1 872 5888271 **SECTION 2: Hazards identification** - 2.1 Classification of the substance or mixture - Classification according to Regulation (EC) No 1272/2008 Skin Irrit. 2 H315 Causes skin irritation. Eye Irrit. 2 H319 Causes serious eye irritation. STOT SE 3 H335 May cause respiratory irritation. - 2.2 Label elements - Labelling according to Regulation (EC) No 1272/2008 The product is classified and labelled according to the CLP regulation. - Hazard pictograms GHS07 - Signal word Warning - Hazard-determining components of labelling: Exo-1,7,7-trimethylbicyclo[2.2.1]hept-2-yl methacrylate - Hazard statements

H315 Causes skin irritation.

H319 Causes serious eye irritation.

H335 May cause respiratory irritation.

Precautionary sta	atements
P261	Avoid breathing vapours.
P280	Wear protective gloves / eye protection.
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.
P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if
	present and easy to do. Continue rinsing.
P312	Call a POISON CENTER/doctor if you feel unwell.
P332+P313	If skin irritation occurs: Get medical advice/attention.
	$(C_{out}, d_{out}, $

(Contd. on page 2) - CH-EN

Printing date 10.04.2023

Version number 3 (replaces version 2)

Revision: 10.04.2023

(Contd. of page 1)

Trade name: 1090

- Additional information:

EUH208 Contains 2-ethylhexanoic acid, cobalt salt. May produce an allergic reaction.

-2.3 Other hazards

- Results of PBT and vPvB assessment

- **PBT:** Not applicable.
- vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

-3.2 Mixtures

- Description: Adhesive

- Dangerous components:				
	Exo-1,7,7-trimethylbicyclo[2.2.1]hept-2-yl methacrylate	> 50 - ≤ 100%		
EINECS: 231-403-1	Skin Irrit. 2, H315; Eye Irrit. 2, H319; STOT SE 3, H335			
CAS: 13586-82-8	2-ethylhexanoic acid, cobalt salt	≥ 0.1 - < 0.25%		
EINECS: 237-015-9	Aquatic Chronic 2, H411; Acute Tox. 4, H302; Skin Irrit. 2, H315; Skin Sens. 1, H317			
- Additional information: For the wording of the listed hazard phrases refer to section 16.				

SECTION 4: First aid measures

-4.1 Description of first aid measures

- General information: Remove any clothing soiled by the product.

- After inhalation:

Supply fresh air. If required, provide artificial respiration. Keep patient warm. Consult doctor if symptoms persist.

In case of unconsciousness place patient stably in side position for transportation.

- After skin contact:

After contact with skin, wash immediately with plenty of soap and water.

If skin irritation continues, consult a doctor.

- After eye contact:

In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

- After swallowing:

Rinse out mouth and then drink plenty of water.

If swallowed, do not induce vomiting: seek medical advice immediately and show this container or label.

- 4.2 Most important symptoms and effects, both acute and delayed

No further relevant information available.

- 4.3 Indication of any immediate medical attention and special treatment needed

No further relevant information available.

SECTION 5: Firefighting measures

- 5.1 Extinguishing media

- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.

- 5.2 Special hazards arising from the substance or mixture

Formation of toxic gases is possible during heating or in case of fire.

In case of fire, the following can be released:

Nitrogen oxides (NOx)

Carbon monoxide and carbon dioxide

Danger of forming toxic pyrolysis products.

Under certain fire conditions, traces of other toxic gases cannot be excluded.

- 5.3 Advice for firefighters

- Protective equipment:

Wear self-contained respiratory protective device.

Do not inhale explosion gases or combustion gases.

(Contd. on page 3)

- CH-EN

Printing date 10.04.2023

Version number 3 (replaces version 2)

Revision: 10.04.2023

(Contd. of page 2)

Trade name: 1090

- Additional information

Cool endangered receptacles with water spray.

Dispose of fire debris and contaminated fire fighting water in accordance with official regulations.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Ensure adequate ventilation Use respiratory protective device against the effects of fumes/dust/aerosol. Avoid contact with the eyes and skin.
 - 6.2 Environmental precautions: Inform respective authorities in case of seepage into water course or sewage system.
- Do not allow product to reach sewage system or any water course. - 6.3 Methods and material for containment and cleaning up: Ensure adequate ventilation. Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).

Dispose of the material collected according to regulations.

- 6.4 Reference to other sections
- See Section 7 for information on safe handling.
- See Section 8 for information on personal protection equipment.
- See Section 10 for information on "stability and reactivity".
- See Section 13 for disposal information.

SECTION 7: Handling and storage

- 7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace. Ensure good interior ventilation, especially at floor level. (Fumes are heavier than air).
- Information about fire - and explosion protection:

- No special precautions are necessary if used and stored according to specifications.
- 7.2 Conditions for safe storage, including any incompatibilities
- Storage:
- Requirements to be met by storerooms and receptacles: Store only in the original receptacle.
- Information about storage in one common storage facility: Not required.
- Further information about storage conditions:
- Store in cool, dry conditions in well sealed receptacles.
- Protect from heat and direct sunlight.
- Store receptacle in a well ventilated area.
- Storage class (TRGS 510, Storage of hazardous substances in non-stationary containers): 10-13
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

- -8.1 Control parameters
- Ingredients with limit values that require monitoring at the workplace:

The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace.

- Additional information: The lists valid during the making were used as basis.
- 8.2 Exposure controls
- Appropriate engineering controls No further data; see section 7.
- Individual protection measures, such as personal protective equipment
- General protective and hygienic measures:

The usual precautionary measures are to be adhered to when handling chemicals.

Keep away from foodstuffs, beverages and feed.

Immediately remove all soiled and contaminated clothing

(Contd. on page 4)

⁻ CH-EN -

Version number 3 (replaces version 2)

Trade name: 1090

Printing date 10.04.2023

Wash hands before breaks and at the end of work. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A/P2 - Hand protection Protective gloves (EN 374) Check protective gloves prior to each use for their proper condition. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the impermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the impermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the impermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the inpermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the impermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the impermeable and resistant to the product/ the substance/ the preparation. Selection of the gloves the impermeable and resistant to the product of substance/ the preparation. Selection of the gloves the impermeable and resistant to the product of substance/ the preparation. Premeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Premeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb&kled.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from maurfacturer to mantfecturer. As the product is a preparation of several substances, the resistance of the				
A void contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter AP2 Hand protection Protective gloves (CN 374) Check protective gloves (CN 374) Check protective gloves prior to each use for their proper condition. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation • Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitril 11, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril 11, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril 11, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril 11, Nr. 0743 Nitril V1, Nr. 0590 Buryl, Nr. 0890 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril 11, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril 11, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril 11, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kel.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, diverses The exact from from manufacturer to manufacturer. As the product is a preparation of several substances, diverses SECTION 9: Physical and chemical properties • Otiour: Characteristic Odour: Characteristic • Otiour: Characteristic • Otiour: Characteristic • Otiour: Characteristic • Ot	Wash hands before breaks and at the end of work	(Contd. of page 3)		
 Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A/P? Hand protection Protective gloves (EN 374) Check protective gloves (EN 374) Check protective gloves nearerial as to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation - Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: . .				
Use suitable respiratory protective device in case of insufficient ventilation. Filter A/P2 Hand protection Protective gloves prior to each use for their proper condition. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Find below a list of appropriate protective gloves for chemical surrounding:				
Filter AP2 Hand protection Protective gloves (EN 374) Check protective gloves (EN 374) Check protective gloves more to each use for their proper condition. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitril II, Nr. 0730, 0730, 0730, 0730, 0730, 0730, 0739, 0739, 0739 oder 0836 Nitril II, Nr. 0743 Nitril II, Nr. 0743 Viton, Nr. 0890 Butyl II, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Pyeface protection Safety glasses SECTION 9: Physical and chemical properties General Information Chour: Characteristic Odour threshold: Not determ		nsufficient ventilation		
 Hand protection Protective gloves (EN 374) Check protective gloves prior to each use for their proper condition. The glove material has to be impermeable and resistant to the product' the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitril I, Nr. 0730, 0732, 0736, 0737, 0738, 0739, 0039 oder 0836 Nitril I, Nr. 0754 Vitril I, Nr. 0754 Vitril I, Nr. 0789 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren, Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 Oftoropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 Oftoropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 Oftoropren, Nr. 0720, 0722, 0723, 0726 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 Nr. esclection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Perteration time / glove material properties SECTION 9: Physical and chemical properties Oclour: Characteristic	1 1 1			
Protective gloves (EN 374) Check protective gloves prior to each use for their proper condition. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitril IN, ro. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril III, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril III, Nr. 0730, 0732, 0737, 0738, 0739 oder 0836 Nitril VI, Nr. 0890 Butyl, Nr. 0897 Butyl, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex I, Nr. 0395 oder 0403 Chloropren, Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kel.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. Penetration time / glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time / glove material can not be advelutation i davance and has therefore to be checked prior to the application. Penetration time / glove material Permeation time / glove material can ot be advelutation time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Pyefrace protection Safety glasses SECTION 9: Physical and chemical properties - General Information Chara				
Check protective gloves prior to each use for their proper condition. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Find belove a list of appropriate protective gloves for chemical surrounding: . Permeation time / penetration time: = 480 minutes (DIN EN 374): Nirril II, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nirril III, Nr. 0743 Nirril VI, Nr. 0743 Nirril VI, Nr. 0743 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nirril II, Nr. 0890 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nirril II, Nr. 0717 . Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex I, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nirril II, Nr. 0740, 0741, 0742 oder 0759 . of KCL company (e-mail: vertrieb@ckl.de) The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material Permeation time / sectored the chemical properties SECTION 9: Physical and chemical properties General Information Characteristic Odour: Red-brown Characteristic Odour: Red-brown Characteristic Odour: Particular Devention Characteristic Odour: Particular Devention Parti				
The glove material has to be impermeable and resistant to the product the substance? the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Find below a list of appropriate protective gloves for chemical surrounding:		oper condition		
Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation • Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: • • • • • • • • • • • • • • • • • • •				
 Material of gloves Find below a list of appropriate protective gloves for chemical surrounding: Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitri II, Nr. 0730, 0732, 0736, 0736, 0737, 0738, 0739 oder 0836 Nitri II, Nr. 0743 Nitri IV, Nr. 0754 Viton, Nr. 0890 Butyl, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0712, 0722, 0722, 0725, oder 0726 Nitri II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and variacturer to manufacturer. As the product is a preparation of several substances, the application. Penetration time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Perfect protection Safety glasses SECTION 9: Physical and chemical properties General Information				
Find below a list of appropriate protective gloves for chemical surrounding: . Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitrii II, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitrii III, Nr. 0743 Nitrii VI, Nr. 0754 Viton, Nr. 0890 Buryl II, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitrii II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitrii II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitrii II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. SECTION 9: Physical and chemical properties General Information Colour: Characteristic Odiour threshold: Not determined. Boiling point or initial boiling point and boiling range Flammability Not applicable.		e penetration times, rates of antusion and the degradation		
Permeation time / penetration time: = 480 minutes (DIN EN 374): Nitri II, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitri IV, Nr. 0743 Nitri IV, Nr. 0754 Viton, Nr. 0890 Butyl II, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex I, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time / glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. SECTION 9: Physical and chemical properties General Information Colour: Characteristic Odour threshold: Odour threshold: Odour		chemical surrounding.		
Nitril I, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril III, Nr. 0743 Nitril IV, Nr. 0754 Viton, Nr. 0890 Butyl, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permetation time is eabove (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour:		enemieur surrounumg.		
Nitril I, Nr. 0730, 0732, 0733, 0736, 0737, 0738, 0739 oder 0836 Nitril III, Nr. 0743 Nitril IV, Nr. 0754 Viton, Nr. 0890 Butyl, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permetation time is eabove (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour: Colour:	Permeation time / penetration time: = 480 minutes (Γ	DIN EN 374):		
Nitril III, Nr. 0743 Nitril VI, Nr. 0890 Butyl II, Nr. 0897 Butyl II, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material enertration time of glove material Permetation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Penetration time of glove material Permetation safety glasses SECTION 9: Physical and chemical properties - 9.1 Information on basic physical and chemical properties - General Information - Colour: - Colour: 				
Nitril VI, Nr. 0754 Viton, Nr. 0890 Butyl II, Nr. 0897 Butyl, Nr. 0898				
Viton, Nr. 0890 Butyl II, Nr. 0897 Butyl, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex I, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties General Information Colour: Characteristic Odour threshold: Not determined. Not determined. Flammability Not applicable.				
Butyl II, Nr. 0897 Butyl, Nr. 0898 Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendation. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties General Information Colour: Colour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and boiling range Characteristic Characteristic Condetermined. Primeability				
Butyl, Nr. 0898 . Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 . Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de) The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material annot be calculated in advance and has therefore to be checked prior to the application. Penetration time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties General Information Colour: Colour: Red-brown Odour: Odour: Colour: Colo				
Permeation time / penetration time: = 240 minutes (DIN EN 374): Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlates I, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Everface protection Safety glasses SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Colour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Pianmability Not applicable.				
Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed Eve/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Colour: - Characteristic - Odour threshold: - Melting point/freezing point: - Odour threshold: - Melting point or initial boiling point and boiling range - Flammability - Not applicable.				
Chloropren Nitril II, Nr. 0717 Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex 1, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed Eve/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Colour: - Characteristic - Odour threshold: - Melting point/freezing point: - Odour threshold: - Melting point or initial boiling point and boiling range - Flammability - Not applicable.	Permeation time / penetration time: = 240 minutes (D	DIN EN 374):		
Permeation time / penetration time: = 120 minutes (DIN EN 374): Naturlatex I, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Colour: - Odour: - Characteristic - Odour: - Odour threshold: - Odour threshold: - Melting point or initial boiling point and boiling range - Flammability - Not applicable.		·		
Naturlatex I, Nr. 0395 oder 0403 Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Permetation time of glove material Permetation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. - Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Colour: Red-brown - Odour threshold: Not determined. - Odour: Undetermined. - Odour threshold: Not determined. - Boiling point or initial boiling point and boiling Undetermined.				
Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726 Nitril II, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. • Eye/face protection Safety glasses SECTION 9: Physical and chemical properties • General Information • Odour: • Odour: • Odour: • Odour threshold: • Melting point/freezing point: • Melting point or initial boiling point and boiling range • Flammability • Not applicable.		DIN EN 374):		
Nitril IÎ, Nr. 0740, 0741, 0742 oder 0759 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties General Information Colour: Characteristic Odour threshold: Not determined. Meting point or initial boiling point and boiling range Informability Not applicable.				
 of KCL company (e-mail: vertrieb@kcl.de). The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Odour: - Odour: - Odour: - Odour: - Odour: - Odour threshold: - Not determined. - Melting point or initial boiling point and boiling - range - Undetermined. - Flammability 	Chloropren, Nr. 0720, 0722, 0723, 0725 oder 0726			
The recommendation is based exclusively on the chemical compatibility and the test according to EN374 under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. • Eye/face protection Safety glasses SECTION 9: Physical and chemical properties • General Information • Colour: Red-brown • Oddur: Characteristic • Odour: Not determined. • Melting point/freezing point: Undetermined. • Melting point or initial boiling point and boiling range Undetermined. • Flammability Not applicable.	Nitril II, Nr. 0740, 0741, 0742 oder 0759			
under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties General Information Colour: Colour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Flammability Not applicable.	of KCL company (e-mail: vertrieb@kcl.de).			
under laboratory conditions. Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties General Information Colour: Colour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Flammability Not applicable.				
Requirements can vary according to the use. Therefore, please always take into account the glove supplier's recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. • Eye/face protection Safety glasses SECTION 9: Physical and chemical properties • General Information • Colour: Red-brown • Odour threshold: Not determined. • Melting point/freezing point: Undetermined. • Boiling point or initial boiling point and boiling range Undetermined. • Flammability Not applicable.		hemical compatibility and the test according to EN374		
recommendations. The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Colour: - Odour: - Odour: - Odour: - Odour: - Odour threshold: - Melting point/freezing point: - Boiling point or initial boiling point and boiling range - Flammability Not applicable.				
The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. - Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. - Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - General Information - Colour: - Odour: - Odour: - Odour: - Odour threshold: - Melting point/freezing point: - Melting point/freezing point: - Boiling point or initial boiling point and boiling range - Flammability Not applicable.	Requirements can vary according to the use. Therefore, please always take into account the glove supplier's			
and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties -9.1 Information on basic physical and chemical properties -9.1 Information on basic physical and chemical properties -9.1 Information Colour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range Undetermined. Flammability Not applicable.				
resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties 9.1 Information Colour: Co				
application. Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties -9.1 Information on basic physical and chemical properties -9.1 Information on basic physical and chemical properties -9.1 Information Colour: Colour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range Undetermined. Flammability Not applicable.				
 Penetration time of glove material Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Colour: Red-brown Odour: Odour threshold: Not determined. Melting point/freezing point: Undetermined. Flammability Not applicable. 		d in advance and has therefore to be checked prior to the		
Permeation time / penetration time: see above (material of gloves) The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. - Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - 9.1 Information on basic physical and chemical properties - General Information - Colour: Red-brown - Odour: Characteristic - Odour threshold: Not determined. - Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range - Flammability Not applicable.				
The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. - Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - 9.1 Information on basic physical and chemical properties - General Information - Colour: Red-brown - Odour: Characteristic - Odour threshold: Not determined. - Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range - Flammability Not applicable.				
observed. - Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - 9.1 Information on basic physical and chemical properties - General Information - Colour: Red-brown - Odour: Characteristic - Odour threshold: Not determined. - Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range Undetermined. - Flammability Not applicable.				
- Eye/face protection Safety glasses SECTION 9: Physical and chemical properties - 9.1 Information on basic physical and chemical properties - General Information - Colour: Red-brown - Odour: Characteristic - Odour threshold: Not determined. - Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range Undetermined. - Flammability Not applicable.	• •	the manufacturer of the protective gloves and has to be		
SECTION 9: Physical and chemical properties - 9.1 Information on basic physical and chemical properties - General Information Red-brown - Colour: Red-brown - Odour: Characteristic - Odour threshold: Not determined. - Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range - Flammability Not applicable.				
-9.1 Information on basic physical and chemical properties - General Information - Colour: Red-brown - Odour: Characteristic - Odour threshold: Not determined. - Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range - Flammability Not applicable.	- Eye/face protection Safety glasses			
- General InformationRed-brown- Colour:Red-brown- Odour:Characteristic- Odour threshold:Not determined Melting point/freezing point:Undetermined Boiling point or initial boiling point and boiling rangeUndetermined FlammabilityNot applicable.	SECTION 9: Physical and chemical prop	erties		
- General InformationRed-brown- Colour:Red-brown- Odour:Characteristic- Odour threshold:Not determined Melting point/freezing point:Undetermined Boiling point or initial boiling point and boiling rangeUndetermined FlammabilityNot applicable.	- 9.1 Information on basic physical and chemical pr	onerties		
- Colour:Red-brown- Odour:Characteristic- Odour threshold:Not determined Melting point/freezing point:Undetermined Boiling point or initial boiling point and boiling rangeUndetermined FlammabilityNot applicable.				
- Odour:Characteristic- Odour threshold:Not determined Melting point/freezing point:Undetermined Boiling point or initial boiling point and boiling rangeUndetermined FlammabilityNot applicable.		Red-brown		
- Melting point/freezing point:Undetermined Boiling point or initial boiling point and boiling rangeUndetermined FlammabilityNot applicable.	- Odour:			
- Melting point/freezing point: Undetermined. - Boiling point or initial boiling point and boiling range Undetermined. - Flammability Not applicable.	- Odour threshold:	Not determined.		
 Boiling point or initial boiling point and boiling range Flammability Not applicable. 		Undetermined.		
rangeUndetermined FlammabilityNot applicable.				
- Flammability Not applicable.	o. o. o	Undetermined.		
		Not applicable.		
(Contd. on page 5)				
		CH-EN		

Printing date 10.04.2023

Version number 3 (replaces version 2)

Revision: 10.04.2023

Trade name: 1090

	(Contd. of page
- Lower and upper explosion limit	
- Lower:	Not determined.
- Upper:	Not determined.
- Flash point:	>100 °C
- Decomposition temperature:	Not determined.
-pH	Not determined.
- Viscosity:	
- Kinematic viscosity	Not determined.
- Kinematic viscosity	
- Dynamic at 20 °C:	5 mPas
- Solubility	
- water:	Not miscible or difficult to mix.
- Partition coefficient n-octanol/water (log value)	Not determined.
- Vapour pressure:	Not determined.
	Not determined.
- Vapour pressure:	
- Density and/or relative density	0.06 s/sm^3
- Density at 20 °C:	0.96 g/cm ³ Not determined.
- Relative density	
- Vapour density	Not determined.
- 9.2 Other information	
- Appearance:	
- Form:	Fluid
 Important information on protection of health an environment, and on safety. 	d
- Ignition temperature:	Product is not self-igniting.
- Explosive properties:	Product does not present an explosion hazard.
- Change in condition	
- Softening point/range	
- Oxidising properties	Not determined.
- Evaporation rate	Not determined.
- Information with regard to physical hazard classe	28
- Explosives	Void
- Flammable gases	Void
- Aerosols	Void
- Oxidising gases	Void
- Gases under pressure	Void
- Flammable liquids	Void
- Flammable inquitis	Void
- Flammable solids	Void
- Sen-reactive substances and mixtures - Pyrophoric liquids	Void
	Void
- Pyrophoric solids	
- Self-heating substances and mixtures	Void
- Substances and mixtures, which emit flammable	T 7 '1
gases in contact with water	Void
- Oxidising liquids	Void
- Oxidising solids	Void
- Organic peroxides	Void
- Corrosive to metals	Void Void
- Desensitised explosives	

SECTION 10: Stability and reactivity

- 10.1 Reactivity No further relevant information available.

(Contd. on page 6) CH-EN

Printing date 10.04.2023

Version number 3 (replaces version 2)

Revision: 10.04.2023

(Contd. of page 5)

Trade name: 1090

- 10.2 Chemical stability
- Thermal decomposition / conditions to be avoided:

No decomposition if used and stored according to specifications.

- Protect from heat and direct sunlight.
- 10.3 Possibility of hazardous reactions Exothermic polymerisation.
- 10.4 Conditions to avoid No further relevant information available.
- 10.5 Incompatible materials: No further relevant information available.
- 10.6 Hazardous decomposition products:

No dangerous products of decomposition if used and stored according to specifications.

SECTION 11: Toxicological information

- 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

- Acute toxicity Based on available data, the classification criteria are not met.
- Skin corrosion/irritation
- Causes skin irritation.
- Serious eye damage/irritation
- Causes serious eye irritation.
- Respiratory or skin sensitisation May produce an allergic reaction.
- Germ cell mutagenicity Based on available data, the classification criteria are not met.
- Carcinogenicity Based on available data, the classification criteria are not met.
- Reproductive toxicity Based on available data, the classification criteria are not met.
- STOT-single exposure
- May cause respiratory irritation.
- STOT-repeated exposure Based on available data, the classification criteria are not met.
- Aspiration hazard Based on available data, the classification criteria are not met.
- Additional toxicological information:
- No experimentally found toxicological data are available for this preparation.
- 11.2 Information on other hazards
- Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

- -12.1 Toxicity
- Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- vPvB: Not applicable.
- 12.6 Endocrine disrupting properties
- The product does not contain substances with endocrine disrupting properties.
- 12.7 Other adverse effects No further relevant information available.
- Additional ecological information:
- General notes:

Water hazard class 2 (German Regulation) (Self-assessment): hazardous for water

Danger to drinking water if even small quantities leak into the ground.

Do not allow product to reach ground water, water course or undiluted sewage system.

SECTION 13: Disposal considerations

- 13.1 Waste treatment methods
- Recommendation Disposal must be made according to official regulations.

(Contd. on page 7)

Printing date 10.04.2023

Version number 3 (replaces version 2)

Revision: 10.04.2023

(Contd. of page 6)

Trade name: 1090

- Uncleaned packaging:

- **Recommendation:** Disposal must be made according to official regulations.

SECTION 14: Transport information	n
- 14.1 UN number or ID number - ADR, IMDG, IATA	Void
- 14.2 UN proper shipping name - ADR, IMDG, IATA	Void
- 14.3 Transport hazard class(es)	
- ADR, ADN, IMDG, IATA - Class	Void
- 14.4 Packing group - ADR, IMDG, IATA	Void
- 14.5 Environmental hazards:	Not applicable.
- 14.6 Special precautions for user	Not applicable.
- 14.7 Maritime transport in bulk according to instruments	o IMO Not applicable.
- UN "Model Regulation":	Void

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

- National regulations:

- Waterhazard class: Water hazard class 2 (Self-assessment): hazardous for water.

- 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

- Relevant phrases

H302 Harmful if swallowed.

- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H319 Causes serious eye irritation.
- H335 May cause respiratory irritation.

H411 Toxic to aquatic life with long lasting effects.

- Abbreviations and acronyms:

ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association

GHS: Globally Harmonised System of Classification and Labelling of Chemicals

- EINECS: European Inventory of Existing Commercial Chemical Substances
- ELINCS: European List of Notified Chemical Substances

CAS: Chemical Abstracts Service (division of the American Chemical Society)

PBT: Persistent, Bioaccumulative and Toxic

- vPvB: very Persistent and very Bioaccumulative
- Acute Tox. 4: Acute toxicity Category 4 Skin Irrit. 2: Skin corrosion/irritation – Category 2
- Eye Irrit. 2: Serious eye damage/eye irritation Category 2
- Skin Sens. 1: Skin sensitisation Category 1

(Contd. on page 8)

Printing date 10.04.2023

Version number 3 (replaces version 2)

Revision: 10.04.2023

Trade name: 1090

	(
STOT SE 3: Specific target organ toxicity (single exposure) – Category 3	
Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard - Category 2	
- * Data compared to the previous version altered.	

(Contd. of page 7)

- CH-EN -